



Gyproc TriLine

Product Data Sheet

Introduction

Characteristics

Gyproc WallBoard factory-bonded to CFC and HCFC-free glass mineral wool backing, meaning zero ODP (Ozone Depletion Potential), Global Warming Potential (GWP) <5.

Gyproc WallBoard consists of an aerated gypsum core encased in, and firmly bonded to strong paper liners. The glass mineral wool insulant is then further bonded to the finished plasterboard. Gyproc WallBoard is a plasterboard that is suitable for drylining internal surfaces.

Applications

Used to upgrade the acoustic performance of masonry walls, whilst also providing some improvement to thermal insulation.

Board colour

- Ivory face paper
- Yellow glass mineral wool backing

Board printing

Face - screw centre markings 'x'.

Edge - product code, EAN number, board thickness x width x length, edge type.

Reverse - none.

Board range

Width mm	Length mm	Edge type
52mm board		Kg/m ² = 13 R (m ² K/W) = 1.25
900	2400	T/E

T/E = Tapered Edge.

Finishing

Board types

T/E - with Gyproc jointing materials for taped and filled joints or application of Thistle Board Finish or Thistle Multi-Finish plaster.

Plastering

The face (ivory) of Gyproc TriLine can be plastered with either Thistle Board Finish or Thistle Multi-Finish. There should be the minimum of delay between completion of the lining and the commencement of plastering.

Jointing

Gyproc jointing materials produce durable joint reinforcement and a smooth, continuous, crack-resistant surface ready for priming and final decoration. A number of jointing specifications are available to suit the board type, method of application, and site preference.

Decoration

After the joint treatment has dried, decoration, including any decorator's preparatory work, should follow with the minimum delay.

Repair

Minor damage - Lightly sand the surface to remove burrs and fill flush with Gyproc Easi-Fill or Gyproc Easi-Fill 45, or two applications of Gyproc Joint Cement. When dry, apply Gyproc Drywall Primer or Gyproc Drywall Sealer to leave the surface ready for decoration.

Deep indents resulting from impact - Check the plasterboard core to ensure that it is not shattered. If intact, apply a coat of Gyproc Joint Filler, or Gyproc Easi-Fill or Gyproc Easi-Fill 45, followed by the procedure for repairing minor damage as outlined above, once set/dry.

Damaged core and/or broken edges (non-performance situations only) - Remove the damaged area of core. Score the liner approximately 10mm away from the sound plaster around the damaged area, and peel the paper liner away. Apply Thistle GypPrime or PVA to seal the core and surrounding liner. Bulk fill the hole with a stiff mix of Gyproc Easi-Fill or Gyproc Easi-Fill 45, or Gyproc Joint Filler, and strike off flush. Apply Gyproc Easi-Fill or Gyproc Easi-Fill 45, or two applications of Gyproc Joint Cement, once the filler is set/dry. When dry, apply Gyproc Drywall Primer or Gyproc Drywall Sealer (only suitable in non-performance situations).

Extensive damage - When the damage is more extensive, it may be necessary to replace that area of plasterboard. It is important that the replacement board is of the same type as specified and installed. Cut out the affected area back to the nearest framing member. Replace the plasterboard, accurately cutting and screw-fixing the same type and thickness of plasterboard. Fill edge joints, then tape and finish in the recommended way. Treat the finished surface with Gyproc Drywall Primer or two coats of Gyproc Sealer, if previously specified for vapour control purposes. Redecorate as required.

NB It is essential that repairs are made 'like for like'. If the finish is skim plaster, jointing materials must not be used in the repair.

EN 13950: 2005 Gypsum Plasterboard, thermal / acoustic insulation composite panel - definitions, requirements and test methods.

Board performance

Fire protection

Plasterboard linings provide good fire protection owing to the unique behaviour of the non-combustible gypsum core when subjected to high temperatures. For the purposes of Building Regulations Approved Document B, plasterboard is designated a 'material of limited combustibility'. The surface of Gyproc TriLine is designated Class 0 (for the purposes of the Building Regulations). Please refer to the table below.

Fire resistance / sound insulation

Please refer to the appropriate WHITE BOOK section for information on the fire resistance and sound insulation of building elements lined with Gyproc TriLine, available to download from www.british-gypsum.com

Reaction to fire test performance

Standard	Performance
BS 476: Part 6: 1989 Method of test for fire propagation for products (plasterboard).	Index of performance (I) not exceeding 12 and a sub-index (i1) not exceeding 6.
BS 476: Part 7: 1997 Surface spread of flame tests for materials (plasterboard).	Class 1.
BS EN 13950 (2005).	B-s1, d0.

Thermal conductivity

- ⚠ Gyproc WallBoard = 0.19W/mK.
- ⚠ Gyproc TriLine Mineral Wool = 0.033W/mK.

Ozone Depletion Potential (ODP)

Zero

Global Warming Potential (GWP)

<5

Effect of temperature

Gyproc TriLine is unsuitable for use in areas subject to continuously damp or humid conditions, i.e. above 70% RH, and must not be used to isolate dampness. Plasterboards are not suitable for use in temperatures above 49°C, but can be subjected to freezing conditions without risk of damage.

Effect of condensation

The thermal insulation and ventilation requirements of the Building Regulations aim to reduce the risk of condensation and mould growth in new buildings. However, designers should take care to eliminate all possibility of problems caused by condensation, particularly in refurbishment projects. For further information, please refer to the WHITE BOOK, available to download from www.british-gypsum.com

General

It is important to observe appropriate health and safety legislation when working on site, i.e. personal protective clothing and equipment, etc. The following notes are intended as general guidance only. In practice, consideration must be given to design criteria requiring specific project solutions.

Handling

Manual off-loading of this product should be carried out with care to avoid unnecessary strain. For further information please refer to the Manual Handling section of the **SITE BOOK** or the Manual Handling Guide, available to download from www.british-gypsum.com

Cutting

This product may be cut using a plasterboard saw. Holes for switch or socket boxes should be cut out before the boards are fixed using a utility saw or sharp knife.

When cutting boards, power and hand tools should be used with care and in accordance with the manufacturers' recommendations. Power tools should only be used by people who have been instructed and trained to use them safely. Appropriate personal protective equipment should be used.

Fixing

Fix boards with decorative side out to receive joint treatment or a skim plaster finish. Lightly butt boards together. Never force boards into position. Install fixings not closer than 13mm from cut edges and 10mm from bound edges. Position cut edges to internal angles whenever possible, removing paper burrs with fine sandpaper. Stagger horizontal and vertical board joints between layers by a minimum of 600mm. Locate boards to the centre line of framing where this supports board edges or ends.

Date of previous version: November 2008.

Gyproc, Thistle, Gypframe and Glasroc are all registered trade names of BPB United Kingdom Limited. Isover is a registered trade name of Saint-Gobain.

Proprietor: BPB United Kingdom Limited registered in England 734396, registered office Saint-Gobain House, Binley Business Park, Coventry, CV3 2TT, UK.

British Gypsum reserves the right to revise product specifications without notice. The information in this document was correct to the best of our knowledge at the time of publication. It is the user's responsibility to ensure that it remains current prior to use. The information in this document is for guidance only and should not be read in isolation. Users should read and familiarise themselves with all the information contained in this document and ensure that they are fully conversant with the products and systems being used, before subsequent specification or installation.

For a comprehensive and up-to-date library of information visit the British Gypsum website at: www.british-gypsum.com

Telephone: 0844 800 1991

Fax: 0844 561 8816

Email: bgtechnical.enquiries@bpb.com

Training enquiries: 0844 561 8810



FM 52358

© British Gypsum December 2009 PDS-019-01