

<b>UK Technical Assessment</b>	<b>0843-UKTA-25/0022 of 28/11/2025</b>
--------------------------------	--

<b>Technical Assessment Body Issuing the UKTA:</b>	UL International (UK) Ltd
<b>Trade name of the construction product</b>	Gyproc Fire Batt / Gyproc Fire Flexi-Board
<b>Product family to which the construction product belongs</b>	Fire Stopping and Sealing Product: <ul style="list-style-type: none"> <li>• Linear Joint and Gap Seals</li> </ul>
<b>Manufacturer</b>	Saint-Gobain Construction Products UK Ltd t/a British Gypsum Saint-Gobain House, East Leake, Loughborough, Leicestershire, LE12 6JU
<b>Manufacturing plant(s)</b>	A/003
<b>This UK Technical Assessment contains</b>	16 pages including 1 Annex which forms an integral part of this assessment.
<b>This UK Technical Assessment* is issued, on the basis of</b>	EAD 350141-00-1106, September 2017.
<b>This version replaces</b>	0843-UKTA-25/0022 issued 30/05/2025

Translations of this UK Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this UK Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

\* in accordance with Construction Products Regulation 2011 as amended by the Construction Products (Amendment etc.) (EU Exit) Regulations 2019 and the Construction Products (Amendment etc.) (EU Exit) Regulations 2020

**Table of Contents**

---

<b>I.</b>	<b>SPECIFIC PARTS OF THE UK TECHNICAL ASSESSMENT</b> .....	<b>3</b>
1	Technical description of the product.....	3
2	Specification of the intended uses of the product in accordance with the applicable UK Assessment Document (Pre-Exit European Assessment Document): EAD 350141-00-1106 .....	3
3	Performance of the product and references to the methods used for its assessment.....	5
4	ASSESSMENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE (HEREINAFTER AVCP) SYSTEM APPLIED, WITH REFERENCE TO ITS LEGAL BASE .....	6
5	Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD.....	6
6	Issued on: .....	7
	<b>ANNEX A – Resistance to Fire Classification – Gyproc Fire Batt</b> .....	<b>8</b>
A.1	Rigid floor constructions with thickness of minimum 150 mm.....	8
A.1.1	Linear joints in a horizontal construction, horizontal linear joints in a vertical construction and horizontal floor joints abutting a wall ...	8
A.1.2	Linear joints in a horizontal construction, horizontal linear joints in a vertical construction and horizontal floor joints abutting a wall ....	9
A.1.3	Linear joints in a vertical construction and horizontal wall joints abutting a floor, ceiling or roof .....	10
A.2	Flexible and rigid wall constructions with wall thickness of minimum 100 mm .....	13
A.3	Raised access floors.....	15
A.3.1	Vertical linear joints between two horizontal constructions .....	15
	<b>ANNEX B – Air Permeability – Gyproc Fire Batt</b> .....	<b>16</b>

## I. SPECIFIC PARTS OF THE UK TECHNICAL ASSESSMENT

### 1 Technical description of the product

- 1) Gyproc Fire Batt/ Gyproc Fire Flexi-Board is a coated mineral wool board used to form linear gap seals where gaps are present. The intended use of Gyproc Fire Batt/ Gyproc Fire Flexi-Board is to reinstate the fire resistance performance of floor to floor/ floor to wall joints and wall gaps. Typical locations of linear joints include floors, the perimeter of floors, walls, ceilings and roofs.
- 2) The Gyproc Fire Batt is supplied coated on one face, referenced 1-S, or on both faces, referenced 2-S. Cut the required board(s) to suit the linear gap dimensions (see Annex A). Unless stated otherwise in Appendix A; All exposed and cut edges of the board must be sealed with Gyproc Acrylic Fire Sealant prior to fitting which will act as an adhesive (optional in rigid constructions). The board(s) must be friction fitted into the gaps with a tight fit. All joints, gaps or imperfections in the installed seal must be filled with Gyproc Acrylic Fire Sealant on the coated exposed side(s) of the board(s).
- 3) Applicant has submitted a written declaration that Gyproc Fire Batt does not contain substances which have to be classified as dangerous according to Directive 67/548/EEC and Regulation (EC) No 1272/2008 and listed in the "Indicative list on dangerous substances" of the EGDS - taking into account the installation conditions of the construction product and the release scenarios resulting from there.

In addition to the specific clauses relating to dangerous substances contained in this United Kingdom Technical Assessment, there may be other requirements applicable to the products falling within its scope (e.g. transposed European and national laws, regulations and administrative provisions). In order to meet the provisions of the Construction Products Regulation, these requirements need also to be complied with, when and where they apply.

- 4) The use category of Gyproc Fire Batt/ Gyproc Fire Flexi-Board in relation to BWR 3 (Hygiene, health and environment) is IA1, S/W2

### 2 Specification of the intended uses of the product in accordance with the applicable UK Assessment Document (Pre-Exit European Assessment Document): EAD 350141-00-1106

Detailed information and data is given in Annex A.

- 1) The intended use of Gyproc Fire Batt/ Gyproc Fire Flexi-Board is to reinstate the fire resistance performance of gaps in and joints between rigid floors and between rigid floors and rigid wall constructions, gaps in and joints between rigid floor constructions, and special applications described in Appendix A.
- 2) The specific elements of construction that the system Gyproc Fire Batt/ Gyproc Fire Flexi-Board may be used to provide a linear joint or gap seal in, are as follows:
  - a) Rigid floors: The floor must have a minimum thickness of 150 mm and comprise aerated concrete, concrete, blockwork or masonry with a minimum density of 650 kg/m<sup>3</sup>.
  - b) Rigid walls: The wall must have a minimum thickness of 100 mm and comprise concrete, aerated concrete blockwork or masonry, with a minimum density of 650 kg/m<sup>3</sup>.

- c) Flexible walls: The wall must have a minimum thickness of 100 mm and comprise steel or timber studs lined on both faces with minimum 2 layers of 12.5 mm thick boards. Apertures are not required to be lined unless stated otherwise in Appendix A. Flexible wall solutions may also be used in rigid walls, with a minimum density of 350 kg/m<sup>3</sup>.

The supporting construction must be classified in accordance with EN 13501-2 for the required fire resistance period. (for details see Annex A)

- 3) The system Gyproc Fire Batt/ Gyproc Fire Flexi-Board may be used to provide a linear joint or gap seal with specific supporting constructions and substrates (for details see Annex A).
- 4) The maximum permitted joint/gap width for system Gyproc Fire Batt/ Gyproc Fire Flexi-Board is 600 mm.
- 5) The maximum movement capability of system Gyproc Fire Batt/ Gyproc Fire Flexi-Board is  $\leq 7.5\%$
- 6) Precautions are required to be taken to prevent a person stepping onto a horizontal linear joint seal or falling against a vertical, or sloped, linear joint seal.
- 7) The provisions made in this UK Technical Assessment are based on an assumed working life of the Gyproc Fire Batt/ Gyproc Fire Flexi-Board of 25 years, provided that the conditions laid down in the product datasheet for the packaging/transport/ storage/installation/use/repair are met. The indications given on the working life cannot be interpreted as a guarantee given by the producer, or the Technical Assessment Body but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.
- 8) Use category: Type Y<sub>1</sub>: Intended for use at temperatures below 0°C with exposure to UV but no exposure to rain. Includes lower classes Y<sub>2</sub>, Z<sub>1</sub>, Z<sub>2</sub>.

### 3 Performance of the product and references to the methods used for its assessment

Product-type: Fire Rated Board		Intended use: Linear Joint & Gap Seal
Basic requirement for construction work	Essential characteristic	Performance
<b>BWR 2 Safety in case of fire</b>		
EN 13501-1	Reaction to fire	D – s1, d0
EN 13501-2	Resistance to fire	Annex A
<b>BWR 3 Hygiene, health and environment</b>		
Declaration of manufacturer & EN 16516	Content, emission and/or release of dangerous substances	Use categories: IA1, S/W2 Declaration of manufacturer
EN 1026:2000	Air permeability (material property)	Annex B
EAD 350141-00-1106, Annex C & EN 12390-8	Water permeability (material property)	No performance determined
<b>BWR 4 Safety in use</b>		
EOTA TR 001:2003	Mechanical resistance and stability #	Pass
EOTA TR 001:2003	Resistance to impact/movement	No performance determined
EOTA TR 001:2003 ISO 11600 & EAD 350141-00-1106, Clause 2.2.13	Adhesion	No performance determined
EAD 350141-00-1106, Clause 2.2.12	Durability	Y <sub>1</sub>
EAD 350141-00-1106, Clause 2.2.13	Movement capacity	No performance determined
EAD 350141-00-1106, Clause 2.2.14	Cycling of perimeter seals for curtain walls	No performance determined
EAD 350141-00-1106, Clause 2.2.15	Compression set	No performance determined
EAD 350141-00-1106, Clause 2.2.16	Linear expansion on setting	No performance determined
<b>BWR 5 Protection against noise</b>		
EN 10140-1,2,4,5/ EN ISO 717-1	Airborne sound insulation*	No performance determined
<b>BWR 6 Energy economy and heat retention</b>		
EN 12664, EN 12667, EN 12939, EN ISO 8990, EN ISO 6946, EN ISO 10456	Thermal properties	No performance determined
EN ISO 12572, EN 12086, EN ISO 10456	Water vapour permeability	No performance determined
# Impact tests were conducted with single Gyproc Fire Batt 50mm 2-S and is relevant for 50mm Fire Batt or thicker		

**4 ASSESSMENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE (HEREINAFTER AVCP) SYSTEM APPLIED, WITH REFERENCE TO ITS LEGAL BASE**

According to the Statutory Instrument 2019 No. 465 – made 5<sup>th</sup> March 2019 and cited as the Construction Products (Amendment etc.) (EU Exit) Regulations 2019 and coming into force on exit day and Statutory Instrument 2020 No. 1359 – made 26<sup>th</sup> November 2020 and cited as the Construction Products (Amendment etc.) (EU Exit) Regulations 2020 and coming into force immediately before the 2019 Regulations come into force, on the procedure for attesting the conformity of construction products as regards fire stopping, fire sealing and fire protective products, published as ‘Pre-Exit’ European Assessment Documents, (see <https://www.gov.uk/guidance/pre-exit-european-assessment-documents-construction-products>), the system of assessment and verification of constancy of performance (see Annex V to Construction Products Regulation 2011 as amended by the Construction Products (Amendment etc.) (EU Exit) Regulations 2019 and the Construction Products (Amendment etc.) (EU Exit) Regulations 2020) given in the following table(s) apply.

<b>Product(s)</b>	<b>Intended use(s)</b>	<b>Level(s) or class(es)</b>	<b>System(s)</b>
Fire stopping and Fire Sealing Products	For fire compartmentation and/or fire protection or fire performance	Any	1

**5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD**

**Tasks of the manufacturer:**

Factory production control

The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall ensure that the product is in conformity with this UK Technical Assessment.

The factory production control shall be in accordance with the Control Plan of 25<sup>th</sup> June 2024 relating to the UK Technical Assessment 0843-UKTA-25/0022 issued on 28/11/2025 which is part of the technical documentation of this UK technical Assessment. The "Control Plan" is laid down in the context of the factory production control system operated by the manufacturer and deposited at UL International (UK) Ltd.

The results of factory production control shall be recorded and evaluated in accordance with the provisions of the Control Plan.

**Other tasks of the manufacturer:**

The manufacturer shall provide a technical data sheet and an installation instruction with the following minimum information:

(a) Technical data sheet:

- Field of application
- Building elements for which the perimeter seal is suitable, type and properties of the building elements like minimum thickness, density, and - in case of lightweight constructions – the construction requirements.
- Limits in size, minimum thickness etc. of the perimeter seal
- Construction of the perimeter seal including the necessary components and additional products (e.g. backfilling material) with clear indication whether they are generic or specific.

(b) Installation instruction:

- Steps to be followed
- Procedure in case of retrofitting
- Stipulations on maintenance, repair and replacement

**6 Issued on:**

**28<sup>th</sup> November 2025**

Report by:



P. Foster  
Project Engineer Associate  
Built Environment

Reviewed by:




D. Forshaw  
Staff Engineer  
Built Environment

**For and on behalf of UL International (UK) Ltd.**

# ANNEX A – Resistance to Fire Classification – Gyproc Fire Batt/ Gyproc Fire Flexi-Board

## A.1 Rigid floor constructions with thickness of minimum 150 mm

### A.1.1 Linear joints in a horizontal construction, horizontal linear joints in a vertical construction and horizontal floor joints abutting a wall



#### A.1.1.1

Substrate	Board(s)	Classification *
masonry/ concrete	60 mm Gyproc Fire Batt 2-S, at any position	<b>E 240 – H – X – F – W120</b> <b>EI 120 – H – X – F – W120</b>
masonry/ concrete/ aluminium	60 mm Gyproc Fire Batt 2-S, at any position	<b>E 120 – H – X – F – W300</b> <b>EI 60 – H – X – F – W300 <sup>1</sup></b>
masonry/ concrete/ aluminium/ steel	60 mm Gyproc Fire Batt 2-S, top face position	<b>E 120 – H – X – F – W600</b> <b>(For EI performance recorded on the seal only, please see note <sup>2</sup> below)</b>
masonry/ concrete/ timber	60 mm Gyproc Fire Batt 2-S, at any position	<b>EI 90 – H – X – F – W600</b>


\*Additional and for information only.

The classifications provided in Table A.1.1.1 consider the insulation performance of all components within the firestopping system as per the requirements of EN 1366-4. This includes temperature evaluation of the metal substrates.

In relation to each of the above classifications, temperatures recorded on the seal (exclusive of the supporting construction) exceeded the maximum allowable after the following times (rounded down):

<sup>1</sup> 90, <sup>2</sup> 120

**A.1.2 Linear joints in a horizontal construction, horizontal linear joints in a vertical construction and horizontal floor joints abutting a wall**



**A.1.2.1**

Substrate	Boards	Classification *
masonry/ concrete	1 x 100 mm Gyproc Fire Batt 1-S	<b>E 240 – H – X – F – W120</b> <b>EI 180 – H – X – F – W120</b>
masonry/ concrete	1 x 100 mm Gyproc Fire Batt 1-S	<b>E 240 – H – X – F – W200</b> <b>EI 240 – H – X – F – W200</b>
masonry/ concrete/ aluminium/ steel		<b>E 240 – H – X – F – W200</b> <b>EI 15 – H – X – F – W200<sup>1</sup></b>

\*Additional and for information only.

The classifications provided in Table A.1.2.1 consider the insulation performance of all components within the firestopping system as per the requirements of EN 1366-4. This includes temperature evaluation of the metal substrates.





In relation to each of the above classifications, temperatures recorded on the seal (exclusive of the supporting construction) exceeded the maximum allowable after the following times (rounded down):


<sup>1</sup> 120

**A.1.3 Linear joints in a vertical construction and horizontal wall joints abutting a floor, ceiling or roof**

**Joint Seal:** Boards fitted to either face of the wall or at any position in between.

Construction details:





### A.1.3.1

Substrate	Boards	Classification*
masonry/ concrete	1 x 60 mm Gyproc Fire Batt 2-S	<b>E 240 – T – X – F – W240</b> <b>EI 90 – T – X – F – W240</b>
	2 x 60 mm Gyproc Fire Batt 2-S with minimum 30 mm air gap in-between	<b>E 240 – T – X – F – W240</b> <b>EI 180 – T – X – F – W240</b>
	1x 100 mm Gyproc Fire Batt 2-S	<b>E 240 – T – X – F – W120</b> <b>EI 180 – T – X – F – W120</b>
	1 x 100 mm Gyproc Fire Batt 2-S	<b>E 240 – V – X – F – W200</b> <b>EI 120 – V – X – F – W200</b>
masonry/ concrete/ timber	1 x 60 mm Gyproc Fire Batt 2-S	<b>EI 60 – T – X – F – W600</b> <b>EI 60 – V – X – F – W600</b>
masonry/ concrete/ gypsum	1 x 60 mm Gyproc Fire Batt 2-S	<b>E 180 – V – X – F – W400</b> <b>EI 120 – V – X – F – W400</b>
masonry/ concrete/ steel	1 x 60 mm Gyproc Fire Batt 2-S	<b>E 120 – T – X – F – W600</b> <b>EI 30 – T – X – F – W600</b> <sup>1</sup>
	1 x 60 mm Gyproc Fire Batt 2-S	<b>E 120 – V – X – F – W600</b> <b>EI 30 – V – X – F – W600</b> <sup>2</sup>
steel/ aluminium	1 x 60 mm Gyproc Fire Batt 2-S	<b>EI 45 – V – X – F – W200</b>

\*Additional and for information only.

The classifications provided in Table A.1.3.1 consider the insulation performance of all components within the firestopping system as per the requirements of EN 1366-4. This includes temperature evaluation of the metal substrates.

In relation to each of the above classifications, temperatures recorded on the seal (exclusive of the supporting construction) exceeded the maximum allowable after the following times (rounded down):





<sup>1</sup> 60, <sup>2</sup> 90


## A.2 Flexible and rigid wall constructions with wall thickness of minimum 100 mm

### A.2.1 Linear joints in a vertical construction and horizontal wall joints abutting a floor, ceiling or roof

**Joint Seal:** Single boards fitted to either face of the wall or at any position in between. Double boards fitted flush on both sides of the wall.

Construction details:





**A.2.1.1**


Substrate	Boards	Classification
flexible wall / rigid wall	2 x 50 mm Gyproc Fire Batt 1-S	<b>EI 120 – T – X – F – W240</b>
lined flexible wall / rigid wall / timber	1 x 60 mm Gyproc Fire Batt 2-S	<b>EI 60 – T – X – F – W600</b> <b>EI 60 – V – X – F – W600</b>
flexible wall * / timber	1 x 60 mm Gyproc Fire Batt 2-S	<b>EI 60 – T – X – F – W600</b> <b>EI 60 – V – X – F – W600</b>

\* Flexible wall must have studs abutting the fire seal.

### A.3 Raised access floors

#### A.3.1 Vertical linear joints between two horizontal constructions

**Joint Seal:** Single board between floor constructions and raised access floors



##### A.3.1.1

Substrate	Application	Board	Classification
masonry/ concrete floors, raised access floors minimum EI 45	Sealed with two $\geq \varnothing$ 5mm beads of Gyproc Fire Adhesive against floor, and two $\geq \varnothing$ 7mm beads of Gyproc Acrylic Fire Sealant against raised access floor	1 x 60 mm Gyproc Fire Batt 2-S	<b>E 120 – T – X – F – W600</b> <b>EI 60 – T – X – F – W600</b>
		1 x 80 mm Gyproc Fire Batt 2-S	<b>EI 90 – T – X – F – W600</b>
		2 x 50 mm Gyproc Fire Batt 1-S, or 1 x 100 mm Gyproc Fire Batt 2-S	<b>EI 120 – T – X – F – W600</b>

## ANNEX B – Air Permeability – Gyproc Fire Batt

Product tested	1200mm high x 600mm wide Gyproc Fire Batt 50mm 2-S		
	Summary of testing procedure		Result
	Pressure (Pa)	Leakage (m <sup>3</sup> /h)	Leakage (m <sup>3</sup> /m <sup>2</sup> /h)
Results under negative chamber pressure	25	0.00	0.00
	50	0.01	0.01
	100	0.02	0.03
	200	0.04	0.06
	300	0.11	0.15
	450	0.49	0.68
	600	0.95	1.32
Results under positive chamber pressure	25	0.00	0.00
	50	0.01	0.01
	100	0.03	0.04
	200	0.08	0.11
	300	0.2	0.28
	450	0.63	0.88
	600	1.01	1.40

