

Installation guidance

ThistlePro® Magnetic

TIMES ARE APPROXIMATE

0 mins



Add approx 8 litres of clean water per 25kg bag to mixing bucket. Gradually add the plaster to water whilst mixing to a preferred consistency



Complete 1st coat at 2-3mm thick

20 mins



Flatten without removing material (large spatulas are useful)

60 - 90 mins



Allow to firm up (approximately 60-70 mins on Gyproc WallBoard)

90 - 120 mins



Mix a fresh batch and apply 2nd coat at 1-2mm thickness

150 mins



Trowel up as needed, avoid using excess water

210 - 240 mins

On the final trowel, use minimal water and avoid over polishing

Note:

Ensure that the product is suitable for the background to which it is being applied by using the Thistle Plaster Selector Guide.

The working characteristics of ThistlePro Magnetic differ from other Thistle finishing plasters. See guidance detailed to the left for more information.



Finishing times are **reduced** by suction



Finishing times are **extended** by cold weather conditions

Times and processes are given as guidance. On site practice may vary.