

# Product Data Sheet

## Gyproc® ProMix Lite

Gyproc ProMix Lite is a lightweight ready mixed air-drying jointing material.

### Where to use

Use it for all stages of hand or mechanical jointing of plasterboard, Glasroc® F MultiBoard, Glasroc F FireCase and Rigidur H.



### Product information

#### Composition

This is a limestone filler with a lightweight aggregate and additives to control rheology and water retention.

#### Colour

Cream.

#### Nominal weight (kg)

20

#### Where to buy

[Click here.](#)

### Performance

Here we only provide performance information related to the product. Please see the White Book online for system-dependent performance.

#### Standards

EN 13963:2005, Type 3A.

Declarations of Performance (DoP) available [Click here.](#)

Reaction to fire	A2-s1, d0
------------------	-----------

#### Limitations of use

Gyproc ProMix Lite is an air-drying product and therefore needs to be left to dry fully before covering.

#### Effect of moisture and condensation

Don't expose the product to moisture repeatedly or for long periods of time, as this can cause it to lose strength and adhesion.

#### Effect of temperature

Ambient and background temperature must be maintained above 5°C until fully dry. The product should be stored between 5°C and 30°C.

# Product Data Sheet

## Gyproc® ProMix Lite

### Application

#### Background preparation: plasterboards

Backgrounds should be reasonably dry, clean and dust-free.

#### Mixing up

Gyproc ProMix Lite is supplied ready mixed with water, at a consistency suitable for hand application. Stir before use, then dilute if necessary. Excessive dilution increases shrinkage and drying times, and reduces strength. Excessive mechanical mixing should be avoided, and only low-speed mixers used.

#### Applying to different substrates

If using Gyproc ProMix Lite for all stages, apply to the joint to embed the tape and immediately overcoat to fully fill the tapered board edges and just feather out onto the board surface. Allow to completely dry, then apply a final coat, feathered out beyond the second. If using as the finishing coat over Gyproc Joint Filler or Gyproc EasiFill, the procedure is similar with the exception that the Joint Filler and EasiFill can be overcoated when set.

### Painting and wallpapering

#### Painting

Apply Gyproc Drywall Primer as soon as practicable after sanding, in preparation for painting.

#### Wallpapering

Apply Gyproc Drywall Sealer as soon as practicable after sanding, in preparation for applying wallcoverings.

#### Tiling

Not suitable as a background for direct application of tiles.

#### Snagging and minor repairs

Minor scratches and dents can be repaired by filling with a new application of this jointing material before redecoration.

Working time: maximum	Not applicable; this is an air-drying and hardens only on evaporation of water.
Set time: minimum	Not applicable; this is an air-drying and hardens only on evaporation of water.
Finish time: minimum	Not applicable; this is an air-drying and hardens only on evaporation of water.
Minimum recommended time before recoating	Wait until product is fully dry.

# Product Data Sheet

## Gyproc® ProMix Lite



### Sitework

#### Storage

Store and use in temperature range of 5-30°C. Avoid stacking more than four tubs high to prevent damage to the packaging.

#### Handling

British Gypsum fully accepts its responsibilities as a supplier of building materials and systems as required by Section 6 of the Health and Safety at Work etc. Act 1974.

To reduce manual handling risk, employers and workers should follow HSE's Manual Handling Operations Regulations 1992 (MHOR) and the HSE's guidance on manual handling at work (INDG143). Employers should carry out a risk assessment and implement control measures to avoid or minimise the need for manual handling. Workers should follow safe lifting and moving techniques and report any hazards.

#### Safety Data Sheet

Safety Data Sheet (SDS) available [Click here](#).

#### Shelf life

This product has a shelf life of 6 months and is marked with a use-by-date.

### Packaging overview

20kg plastic tub, supplied palletised.

Quantity per pallet	40 tubs
---------------------	---------

### Environmental

#### Recyclability

This product cannot be recycled.

#### Disposal

Waste should be disposed of in accordance with local authority requirements. Wet waste should be prevented from entering drains.



**SAINT-GOBAIN**

**British Gypsum**

Head Office, East Leake,  
Loughborough,  
Leicestershire, LE12 6HX  
T: 0115 945 1000  
[british-gypsum.com](http://british-gypsum.com)



"Gyproc", "Thistle", "ThistlePro", "Gypframe" and "Glasroc" are all registered trademarks of Saint-Gobain Construction Products UK Limited. "Isover" is a registered trademark of Saint-Gobain Isover (French legal entity) and "Okarno" is a registered trademark of Okarno Limited.

Saint-Gobain Construction Products UK Limited is a limited company registered in England under company number 734396, having its registered office at Saint-Gobain House, East Leake, Loughborough, Leicestershire, LE12 6JU, UK. Saint-Gobain Construction Products UK Limited trades as British Gypsum for part of its business activities.

British Gypsum reserves the right to revise product specification without notice. The information herein should not be read in isolation as it is meant only as guidance for the user, who should always ensure that they are fully conversant with the products and systems being used and their subsequent installation prior to the commencement of work. For a comprehensive and up-to-date library of information visit the British Gypsum website at: [british-gypsum.com](http://british-gypsum.com). For information about products supplied by Okarno Limited or Saint-Gobain Isover please see their respective websites.

"British Gypsum" is a registered trademark of Saint-Gobain Construction Products UK Limited.