

# Product Data Sheet

## Thistle® DriCoat

Thistle DriCoat is a cement based undercoat plaster designed for renovations.

### Where to use

Use it for replastering walls after flooding, or after fitting a new damp proof course. Walls that have dried out after flooding or a new damp proof course contain hygroscopic salts that can absorb moisture and cause persistent damp. Thistle DriCoat stops these salts migrating into the plaster to protect interior decoration from damage. Always finish with Thistle BoardFinish.



### Product information

#### Composition

This is a cement based plaster with waterproofing additives.

#### Colour

Light grey.

#### Nominal weight (kg)

25.

### Performance

Here we only provide performance information related to the product. Please see the White Book online for system-dependent performance.

#### Standards

EN 998-1:2016.

Declarations of Performance (DoP) available [Click here](#).

Reaction to fire	A1
------------------	----

#### Effect of moisture and condensation

Thistle DriCoat is unaffected by exposure to moisture, although finishes including finishing plasters may be unsuitable for moist conditions. Do not use Thistle DriCoat to resist water under hydrostatic pressure.

#### Effect of temperature

Thistle plasters aren't suitable for plastering onto frozen backgrounds. However, you can use them in frosty conditions as long as you prevent the plaster from freezing after it's been applied. Dry, bagged plaster isn't affected by low temperatures.

Once Thistle plasters are fully set and dry, they shouldn't be exposed to temperatures above 49°C. When applying in hot or dry conditions, make sure the plaster doesn't lose water too quickly, as it needs some of the mixing water to set and reach full strength.

### Application

#### Background preparation: solid backgrounds

First identify and eliminate the source of the rising damp. Hack off the existing plasterwork to a height at least 0.5 metres above either the new damp proof course or the last detectable sign of dampness. Where the old plaster is gypsum based, remove it completely.

After injecting a chemical damp proof course, thoroughly rake out old mortar joints in areas with high salt concentrations, then brush the face of the brickwork with a wire brush.

Ideally, you should delay replastering with Thistle DriCoat for as long as possible to allow the background to dry out. Before replastering, carefully remove any salts brought to the surface of the background during drying. Heavy salt contamination in the background can cause persistent damp problems, so Thistle DriCoat shouldn't be used unless a survey shows that the risk from salts is minimal. If there is a high salt concentration, an independent wall lining may be a better solution.

Apply Thistle DriCoat once the background is clean, sound, free from dust and efflorescence, and where only residual moisture is present. Before plastering, treat low suction or smooth backgrounds such as engineering bricks with a water resistant bonding aid; plaster over this according to the manufacturer's recommendations.

Where the background is dry, it's important to control suction by applying water. This prevents the plaster drying too quickly, which would impair its strength.

If the floor is solid, leave a 50mm gap between the plasterwork and the floor level. Don't bridge the damp proof course under any circumstances. Finally, don't use gypsum based materials to fix angle beads.

#### Mixing up

Add Thistle plasters to clean water and use clean mixing equipment, as contamination from previous mixes affects the setting time and strength. Fresh contamination has more of an effect than old, so you should wash equipment just after mixing rather than just before.

Thistle plasters are suitable for mixing by hand or using a mechanical whisk with a slow speed and high torque. Mix for 2-3 minutes until you achieve a smooth homogeneous working consistency. Rest the mix for 3-5 minutes, then remix it back to the right consistency, adding small amounts of water as you need to.

#### Applying to different substrates

Apply the plaster with a firm pressure, and build it out to the required thickness without exceeding 11mm. Rule the plaster to an even surface and lightly scratch it to form a key. Leave a gap of at least 24 hours between applying each coat. Follow good site practice as outlined in BS EN 13914 Code of Practice for Internal Plastering.

#### Finishing

Allow the scratched undercoat to cure and shrink before applying Thistle BoardFinish plaster. In good drying conditions, leave a minimum delay of 24 hours. In cold or damp conditions, or where background suction is low, leave a longer delay. If the delay is not long enough, the finish coat could crack or shell.

Wall application thickness (mm)	11
Coverage per bag (m <sup>2</sup> )	3.25
Set time: minimum	24 hours
Finish time: minimum	24 hours
Water requirements per bag (litres)	15

#### Painting and wallpapering

Add Thistle BoardFinish plaster before decorating. Don't decorate directly onto Thistle DriCoat plaster.

#### Tiling

Add Thistle BoardFinish plaster before tiling. Don't tile directly onto Thistle undercoat plaster.

#### Snagging and minor repairs

Thistle undercoat plaster finished with 2mm of Thistle finishing plaster provides a system that's suitable for moderate to high impact and wear. If the plaster is correctly applied, you shouldn't need to maintain it afterwards.

# Product Data Sheet

Thistle® DriCoat

## Sitework

### Storage

Bags should be stored inside on a flat and stable surface, away from any sources of moisture, heat or direct sunlight. If storing on a concrete floor, use dry timber platforms. The bags should not be stored near any edges, openings, walkways or traffic areas, where they could fall or cause obstruction. Damaged or opened bags should be used first or discarded appropriately.

### Handling

British Gypsum fully accepts its responsibilities as a supplier of building materials and systems as required by Section 6 of the Health and Safety at Work etc. Act 1974.

To reduce manual handling risk, employers and workers should follow HSE's Manual Handling Operations Regulations 1992 (MHOR) and the HSE's guidance on manual handling at work (INDG143). Employers should carry out a risk assessment and implement control measures to avoid or minimise the need for manual handling. Workers should follow safe lifting and moving techniques and report any hazards.

### Safety Data Sheet

Safety Data Sheet (SDS) available [Click here](#).

### Shelf life

Stored correctly, this product has a shelf life of six months, and bags are marked with a use by date so you can use them in strict rotation.

### Packaging overview

This plaster is packaged in a paper bag and is supplied palletised.

Quantity per pallet	40 bags
Pallet: nominal height (mm)	1250
Pallet: nominal length (mm)	1250
Pallet: nominal depth (mm)	1000
Pallet: nominal weight (tonnes)	1.0

## Environmental

### Disposal

Harden the plaster with water and dispose of it according to local authority requirements.



**SAINT-GOBAIN**

**British Gypsum**

Head Office, East Leake,  
Loughborough,  
Leicestershire, LE12 6HX  
T: 0115 945 1000  
[british-gypsum.com](http://british-gypsum.com)



"Gyproc", "Thistle", "ThistlePro", "Gypframe" and "Glasroc" are all registered trademarks of Saint-Gobain Construction Products UK Limited. "Isover" is a registered trademark of Saint-Gobain Isover (French legal entity) and "Okarno" is a registered trademark of Okarno Limited.

Saint-Gobain Construction Products UK Limited is a limited company registered in England under company number 734396, having its registered office at Saint-Gobain House, East Leake, Loughborough, Leicestershire, LE12 6JU, UK. Saint-Gobain Construction Products UK Limited trades as British Gypsum for part of its business activities.

British Gypsum reserves the right to revise product specification without notice. The information herein should not be read in isolation as it is meant only as guidance for the user, who should always ensure that they are fully conversant with the products and systems being used and their subsequent installation prior to the commencement of work. For a comprehensive and up-to-date library of information visit the British Gypsum website at: [british-gypsum.com](http://british-gypsum.com). For information about products supplied by Okarno Limited or Saint-Gobain Isover please see their respective websites.

"British Gypsum" is a registered trademark of Saint-Gobain Construction Products UK Limited.