

Product Data Sheet

Thistle® One Coat Plaster

Thistle One Coat Plaster is a versatile undercoat and finish plaster in one product. It provides a smooth, inert and high quality surface to internal walls and ceilings, as well as a durable base for applying decorative finishes. The plaster is available in a convenient pack size for smaller jobs.

Where to use

Apply the plaster by hand to a range of internal surfaces, including brick, blockwork, plasterboard and concrete finish plaster. It's also ideal for filling larger holes and chasing in. Simply build up the coverage in stages to a maximum of 25mm.



Product information

Composition

This is a retarded hemihydrate, pre-mixed gypsum plaster.

Colour

White.

Nominal weight (kg)

7.5kg and 12.5kg bags.

Performance

Here we only provide performance information related to the product. Please see the White Book online for system-dependent performance.

Standards

EN 13279-1:2008, Type B4/20/2 and C3/20.

Declarations of Performance (DoP) available [Click here](#).

| | |
|---|-------|
| Reaction to fire | A1 |
| Thermal resistance (m ² K/W) | 0.038 |

Effect of moisture and condensation

Don't expose the plaster to moisture repeatedly or for long periods of time, as this can cause it to lose strength and adhesion.

Effect of temperature

Thistle plasters aren't suitable for plastering onto frozen backgrounds. However, you can use them in frosty conditions as long as you prevent the plaster from freezing after it's been applied. Dry, bagged plaster isn't affected by low temperatures.

Once Thistle plasters are fully set and dry, they shouldn't be exposed to temperatures above 49°C. When applying in hot or dry conditions, make sure the plaster doesn't lose water too quickly, as it needs some of the mixing water to set and reach full strength.

Application

Background preparation: plasterboards

Only use Thistle finishing plasters on the face of the board, which is the side without a paper overlap. This doesn't apply to moisture resistant boards. Reinforce joints with Thistle ProTape FT50 or FT100, or with Gyproc Joint Tape.

Background preparation: moisture resistant grade boards

Avoid applying skim plaster to Gyproc Moisture Resistant boards. These boards are designed for environments with high humidity, which can cause the plaster to lose strength and adhesion.

Where moisture resistant boards are used in shell and core construction to provide temporary moisture resistance, it's best to skim them after the building envelope has been made weathertight. Only apply plaster to the face of moisture resistant boards, and pre-treat them with Thistle Bond-it.

Background preparation: Glasroc F MultiBoard and Glasroc F FireCase

Apply Thistle finishing plasters to the smooth face of the board. Application techniques and joint reinforcement are similar to those used on plasterboards.

Background preparation: solid backgrounds

Follow this guidance when working with solid backgrounds:

- Before applying the plaster, use the Thistle Essential Selector Guide to check that the background is suitable.
- Make sure the surface is dry, clean and protected from the weather.
- Before plastering concrete backgrounds, remove any mould, oil or other agents from the surface.
- You don't need to wet no-fines concrete before plastering.
- Allow enough time for normal ballast concrete to mature before applying the plaster.
- Don't apply plaster to 'green' backgrounds, or where any free water is visible.
- Wet mature concrete to displace the air before plastering.
- You may need to use Thistle Bond-it on smooth low suction backgrounds.

Mixing up

Add Thistle plasters to clean water and use clean mixing equipment, as contamination from previous mixes affects the setting time and strength. Fresh contamination has more of an effect than old, so you should wash equipment just after mixing rather than just before.

Thistle plasters are suitable for mixing by hand or using a mechanical whisk with a slow speed and high torque. While mechanical mixing speeds up the process, there is no need to continue mixing after you've dispersed the lumps and reached the right consistency. Over-mixing wastes time and energy, and can affect setting times, reduce workability, and make it difficult to achieve a flat finish.

Application (continued)

Applying to different substrates

Plastering onto board backgrounds

- 1 Before applying Thistle One Coat to Gyproc plasterboards or Glasroc F MultiBoard, Glasroc F Firecase, Ridigur H (pre-treated with Thistle GypPrime) reinforce flat joints using Thistle ProTape FT50 or FT100, or prefill any gaps wider than 3mm and reinforce them using Gyproc Joint Tape. Thistle ProTape FT50 and FT100 fibre tapes are self-adhesive, so you can fix them to the board's surface before the first application of plaster. If you're using Gyproc Joint Tape, embed it in the first coat over each joint, leaving enough plaster under the tape to ensure good adhesion. Then press the tape firmly into the plaster and immediately cover it with a further application.
- 2 Apply plaster to the whole surface after the joint treatment has partially set but not dried. Some joints will experience more movement, such as around door or window apertures, where board edges aren't fully supported, or on ceilings below floors that are susceptible to high deflection. In these areas, embed Gyproc Joint Tape in the finish for better resistance to cracking than with fibre tapes.
- 3 Fix Thistle Thin Coat Angle Beads to plasterboard angles by embedding them in dabs of finish plaster. Avoid fixing the bead to the board 'dry'; this could reduce the adhesion as it's difficult to squeeze plaster between the bead and the plasterboard.
- 4 To hold the bead in alignment as the plaster sets, we recommend you use additional mechanical fixings like non-rusting nails, screws and staples. Wipe any surplus from corners before the plaster sets, as scraping it away later may damage the zinc coating.
- 5 Apply the finish plaster with a firm pressure and build it out to the required thickness in two applications, trowelling to a smooth matt finish as it sets. Follow good site practice as outlined in BS EN 13914 Code of Practice for Internal Plastering.

Plastering onto solid backgrounds

- 1 As part of the preparation, fix all Thistle angle beads in position using Thistle gypsum plaster. Once the angle beads are in place, leave them to set before applying plaster to the rest of the wall.
- 2 Apply the first coat to the background. Once the entire background has been covered, apply a second thin coat over the whole surface. When you've reached the required thickness, the wall can be ruled off. You can then fill any low or hollow spots that have been missed. Once the wall has been levelled, use a spatula to close and flatten the surface.
- 3 When the surface begins to tighten and firm, it's ready to be sponged. Rub a sponge float over the plaster in circular motions to bring the fat to the surface, then leave it until it stiffens. After this, you can do a final trowel for a flat, seamless finish.

Application (continued)

| | |
|---|---|
| Wall application thickness (mm) | 13 |
| Ceiling application thickness (mm) | 10 |
| Gyproc HandiBoard, Gyproc WallBoard and Gyproc Plank: maximum recommended thickness (mm) | 13 (use Thistle Bond-it on moisture resistant boards) |
| Engineering bricks with raked joints: maximum recommended thickness (mm) | 13 |
| Dense aggregate concrete blocks and no-fines concrete: maximum recommended thickness (mm) | 13 (use Thistle Bond-it on smooth, low suction blocks) |
| Normal ballast concrete soffits: maximum recommended thickness (mm) | 13 |
| Other aggregate concrete: maximum recommended thickness (mm) | 13 |
| Precast concrete units and composite ceilings: maximum recommended thickness (mm) | 13 (use Thistle Bond-it) |
| Extended metal lath: maximum recommended thickness (mm) | 13 |
| Backgrounds treated with Thistle Bond-it (e.g. glazed or painted surfaces): maximum recommended thickness (mm) | 13 |
| Expanded polystyrene soffits: maximum recommended thickness (mm) | 13 |
| Expanded polystyrene walls: maximum recommended thickness (mm) | 13 |
| Aerated concrete blocks: maximum recommended thickness (mm) | 13 |
| Common brick walls and concrete bricks with raked joints: maximum recommended thickness (mm) | 13 |
| Painted and tiled surfaces: maximum recommended thickness (mm) | 13 (use Thistle Bond-it) |
| Coverage per bag (m ²) | 0.675 at 13mm thick for 7.5kg bags 1.125 at 13mm thick for 12.5kg bags |
| Working time: maximum | 45 minutes |
| Set time: minimum | 90 minutes |
| Water requirements per bag (litres) | 4.2 for 7.5kg bags 7.5 for 12.5kg bags |
| Dry set weight (kg/m ²) | 12.6 at 13mm thick |

Application (continued)

Painting and wallpapering

Make sure Thistle plasters are thoroughly dry before decorating, although you can apply a coat of permeable paint in the interim. You can decorate the finished surface using most proprietary paint finishes and wall covering adhesives, but always follow the manufacturers' recommendations for the best results.

Tiling

You can apply tiles up to 20kg per m² directly to Thistle finishing plasters, except where the system includes a bonding agent. As the total weight of tiles and plaster applied over a bonding agent is limited to 20kg per m², consider tiling directly to the background instead.

If you're plastering to provide a background for tiles, avoid polishing the surface. If the surface has already been polished, roughen it and use a suitable primer to create a good key for the tile adhesive.

Snagging and minor repairs

Thistle plasters on plasterboard provide a system that's suitable for moderate impact and wear. When used over solid backgrounds, they offer good resistance to minor casual damage, but the resistance to damage from greater impacts depends on the background. If the plaster is correctly applied, you shouldn't need to maintain it afterwards.

Sitework

Storage

Store bags dry, as water causes lumps to form inside. If storing on a concrete floor, use dry timber platforms.

Handling

British Gypsum fully accepts its responsibilities as a supplier of building materials and systems as required by Section 6 of the Health and Safety at Work etc. Act 1974. However, when designing and installing systems that use British Gypsum products, you must consider the legal requirements set out in:

- 1 Manual Handling Operations Regulations
- 2 Construction (Design and Management) Regulations
- 3 Control of Substances Hazardous to Health Regulations (COSHH).

Safety Data Sheet

Safety Data Sheet (SDS) available [Click here](#).

Shelf life

Stored correctly, this product has a shelf life of six months, and bags are marked with a use by date so you can use them in strict rotation.

Packaging overview

This plaster is packaged in a plastic bag and is supplied palletised.

| | |
|---------------------------------|--|
| Quantity per pallet | 100 bags: 7.5kg 72 bags: 12.5kg |
| Pallet: nominal height (mm) | 257 for 7.5kg bags 293 for 12.5kg bags |
| Pallet: nominal length (mm) | 375 for 7.5kg bags 448 for 12.5kg bags |
| Pallet: nominal depth (mm) | 87 for 7.5kg bags 101 for 12.5kg bags |
| Pallet: nominal weight (tonnes) | 0.75 for 7.5kg bags 0.9 for 12.5kg bags |

Product Data Sheet

Thistle® One Coat Plaster

Environmental

Disposal

Segregate the plaster from non-gypsum waste for recycling where possible, and dispose of it according to local authority requirements.



SAINT-GOBAIN

British Gypsum
Head Office, East Leake,
Loughborough,
Leicestershire, LE12 6HX
T: 0115 945 1000



"Gyproc", "Thistle", "ThistlePro", "Gypframe" and "Glasroc" are all registered trademarks of Saint-Gobain Construction Products UK Limited. "Isover" is a registered trademark of Saint-Gobain Isover (French legal entity) and "Artex" is a registered trademark of Saint-Gobain Construction Products UK Limited.

Saint-Gobain Construction Products UK Limited is a limited company registered in England under company number 734396, having its registered office at Saint-Gobain House, East Leake, Loughborough, Leicestershire, LE12 6JU, UK. Saint-Gobain Construction Products UK Limited trades as British Gypsum for part of its business activities.

British Gypsum reserves the right to revise product specification without notice. The information herein should not be read in isolation as it is meant only as guidance for the user, who should always ensure that they are fully conversant with the products and systems being used and their subsequent installation prior to the commencement of work. For a comprehensive and up-to-date library of information visit the British Gypsum website at: british-gypsum.com. For information about products supplied by Artex Limited or Saint-Gobain Isover please see their respective websites.

"British Gypsum" is a registered trademark of Saint-Gobain Construction Products UK Limited.