

Product Data Sheet

ThistlePro® Magnetic

ThistlePro Magnetic is a finish plaster that attracts magnets, letting you hang paintings and other items without fixings. It gives you interactive walls in schools, offices, living spaces, or anywhere where you want to get more creative with your walls.

You can decorate magnetic walls with paint, wallpaper, stickers or specialist finishes such as whiteboard or chalkboard paint without affecting the magnetic attraction.



Where to use

Use ThistlePro Magnetic to finish low suction backgrounds like plasterboard, Glasroc® F MultiBoard, Glasroc F FireCase, Rigidur H (pre-treated with Thistle® GypPrime), flat concrete, and other flat surfaces treated with bonding agents. It's also suitable for medium-high suction gypsum undercoat plasters.

Product information

Composition

This is a retarded hemihydrate, pre-mixed gypsum plaster.

Colour

Dark grey.

Nominal weight (kg)

25.

Where to buy

[Click here.](#)

Performance

Here we only provide performance information related to the product. Please see the White Book online for system-dependent performance.

Standards

EN 13279-1:2008, Type B1/20/2.

Declarations of Performance (DoP) available [Click here.](#)

Reaction to fire	A1
Thermal resistance (m ² K/W)	0.004
Specialist performance	Magnetic attraction.

Effect of moisture and condensation

Don't expose the plaster to moisture repeatedly or for long periods of time, as this can cause it to lose strength and adhesion.

Effect of temperature

Thistle plasters aren't suitable for plastering onto frozen backgrounds. However, you can use them in frosty conditions as long as you prevent the plaster from freezing after it's been applied. Dry, bagged plaster isn't affected by low temperatures.

Once Thistle plasters are fully set and dry, they shouldn't be exposed to temperatures above 49°C. When applying in hot or dry conditions, make sure the plaster doesn't lose water too quickly, as it needs some of the mixing water to set and reach full strength.

ThistlePro® Magnetic

Application

Background preparation: plasterboards

Only use Thistle finishing plasters on the face of the board, which is the side without a paper overlap. This doesn't apply to moisture resistant boards. Reinforce joints with Thistle ProTape FT50 or FT100, or with Gyproc Joint Tape.

Background preparation: undercoats

Leave gypsum based undercoats reasonably flat and with a scratch key. Finish them when they're set but not dry to avoid high suction that needs to be damped down first. Use Thistle GypPrime to pre-treat very high suction backgrounds.

Cement based undercoats shrink when they are dry, and can crack days or even weeks after application. If you apply a Thistle finishing plaster before the shrinkage is complete, it's more likely to crack or delaminate, particularly if the undercoat wasn't keyed enough. Therefore, the key needs to be much better, and the drying time allowance much longer, than for gypsum based undercoats.

Retarded ready mixed cement based mortars may have delayed shrinkage, and may contain additives that interfere with the strength or setting of Thistle finishing plasters.

Background preparation: moisture resistant grade boards

Avoid applying skim plaster to Gyproc Moisture Resistant boards. These boards are designed for environments with high humidity, which can cause the plaster to lose strength and adhesion.

Where moisture resistant boards are used in shell and core construction to provide temporary moisture resistance, it's best to skim them after the building envelope has been made weathertight. Only apply plaster to the face of moisture resistant boards, and pre-treat them with Thistle Bond-it.

Background preparation: Glasroc F MultiBoard and Glasroc F FireCase

Apply Thistle finishing plasters to the smooth face of the board. Application techniques and joint reinforcement are similar to those used on plasterboards.

Mixing up

Add Thistle plasters to clean water and use clean mixing equipment, as contamination from previous mixes affects the setting time and strength. Fresh contamination has more of an effect than old, so you should wash equipment just after mixing rather than just before.

Thistle plasters are suitable for mixing by hand or using a mechanical whisk with a slow speed and high torque. While mechanical mixing speeds up the process, there is no need to continue mixing after you've dispersed the lumps and reached the right consistency. Over-mixing wastes time and energy, and can affect setting times, reduce workability, and make it difficult to achieve a flat finish.

Applying to different substrates

Plastering onto board backgrounds

- 1 Before applying ThistlePro Magnetic to Gyproc plasterboards or Glasroc F MultiBoard, Glasroc F FireCase, Rigidur H (pre-treated with Thistle GypPrime) reinforce flat joints using Thistle ProTape FT50 or FT100, or pre-fill any gaps wider than 3mm and reinforce them using Gyproc Joint Tape. Thistle ProTape FT50 and FT100 fibre tapes are self-adhesive, so you can fix them to the board's surface before the first application of plaster. If you're using Gyproc Joint Tape, embed it in the first coat over each joint, leaving enough plaster under the tape to ensure good adhesion. Then press the tape firmly into the plaster and immediately cover it with a further application.
- 2 Apply plaster to the whole surface after the joint treatment has partially set but not dried. Some joints will experience more movement, such as around door or window apertures, where board edges aren't fully supported, or on ceilings below floors that are susceptible to high deflection. In these areas, embed Gyproc Joint Tape in the finish for better resistance to cracking than with fibre tapes.
- 3 Fix Thistle Thin Coat Angle Beads to plasterboard angles by embedding them in dabs of finish plaster. Avoid fixing the bead to the board 'dry'; this could reduce the adhesion as it's difficult to squeeze plaster between the bead and the plasterboard.
- 4 To hold the bead in alignment as the plaster sets, we recommend you use additional mechanical fixings like non-rusting nails, screws and staples. Wipe any surplus from corners before the plaster sets, as scraping it away later may damage the zinc coating.
- 5 Apply the finish plaster with a firm pressure, and build it out to the required thickness in a minimum of two applications. Trowel it without water to achieve a smooth matt finish as it sets. If blebbing or blistering occurs, use a third coat of 1mm for a superior finish, rather than trowelling the second coat excessively. The overall thickness should be an absolute minimum of 3mm, while 6mm gives you optimum magnetic attraction. Follow good site practice as outlined in BS EN 13914 Code of Practice for Internal Plastering.

ThistlePro® Magnetic

Application (continued)

Wall application thickness (mm)	3-6
Coverage per bag (m ²)	5 at 3mm thick 2.5 at 6mm thick
Working time: minimum	60 minutes
Set time: minimum	200 minutes
Water requirements per bag (litres)	8

Painting and wallpapering

Make sure Thistle plasters are thoroughly dry before decorating, although you can apply a coat of permeable paint in the interim. You can decorate the finished surface using most proprietary paint finishes and wall covering adhesives, but always follow the manufacturers' recommendations for the best results.

Sitework

Storage

Store bags dry, as water causes lumps to form inside. If storing on a concrete floor, use dry timber platforms.

Handling

British Gypsum fully accepts its responsibilities as a supplier of building materials and systems as required by Section 6 of the Health and Safety at Work etc. Act 1974. However, when designing and installing systems that use British Gypsum products, you must consider the legal requirements set out in:

- 1 Manual Handling Operations Regulations
- 2 Construction (Design and Management) Regulations
- 3 Control of Substances Hazardous to Health Regulations (COSHH).

Safety Data Sheet

Safety Data Sheet (SDS) available [Click here](#).

Shelf life

Stored correctly, this product has a shelf life of seven months, and bags are marked with a use by date so you can use them in strict rotation.

Snagging and minor repairs

Thistle finishing plasters on plasterboard provide a system that's suitable for moderate impact and wear. When used over undercoat plasters, they offer good resistance to minor casual damage, but the resistance to damage from greater impacts depends on the undercoat used. If the plaster is correctly applied, you shouldn't need to maintain it afterwards.

Packaging overview

This plaster is packaged in a plastic bag.

Quantity per pallet	24 bags (available also in single bag quantities), up to 4 bags can be added to a load without any change in load make up
Pallet: nominal height (mm)	450
Pallet: nominal length (mm)	1200
Pallet: nominal depth (mm)	1000
Pallet: nominal weight (tonnes)	0.6

Product Data Sheet

ThistlePro® Magnetic



Environmental

Disposal

Segregate the plaster from non-gypsum waste for recycling where possible, and dispose of it according to local authority requirements.

BES 6001 classification

Excellent.

SAINT-GOBAIN

British Gypsum
Head Office, East Leake,
Loughborough,
Leicestershire, LE12 6HX
T: 0115 945 1000



"Gyproc", "Thistle", "Gypframe" and "Glasroc" are all registered trademarks of Saint-Gobain Construction Products UK Limited. "Isover" is a registered trademark of Saint-Gobain Isover and "Artex" is a registered trademark of Saint-Gobain Construction Products UK Limited.

Saint-Gobain Construction Products UK Limited is a limited company registered in England under company number 734396, having its registered office at Saint-Gobain House, East Leake, Loughborough, Leicestershire, LE12 6JU, UK. Saint-Gobain Construction Products UK Limited trades as British Gypsum for part of its business activities.

British Gypsum reserves the right to revise product specification without notice. The information herein should not be read in isolation as it is meant only as guidance for the user, who should always ensure that they are fully conversant with the products and systems being used and their subsequent installation prior to the commencement of work. For a comprehensive and up-to-date library of information visit the British Gypsum website at: british-gypsum.com. For information about products supplied by Artex Limited or Saint-Gobain Isover please see their respective websites.

"British Gypsum" is a registered trademark of Saint-Gobain Construction Products UK Limited.