

Thistle MultiFinish

Installation guidance - times are approximate

0 mins



- Add approx 11.5 litres of clean water per 25kg bag to mixing bucket. Gradually add the plaster to water whilst mixing



- Complete 1st coat (1mm thick)

20 mins



- Complete 2nd coat (total 2mm thick)

45 mins



- Closing in

60 mins

85 mins



- 1st trowel

105 mins



- 2nd trowel

120 mins



- Final trowel (lubricated with minimal water)

Times and processes are given as guidance. On site practice may vary.

— Finishing times are reduced by suction

+ Finishing times are extended by cold weather conditions